

Epoxart Kit 3:1

3:1 EPOXY SYSTEM FOR RESINING, NETTING AND REPAIRING MATERIALS

Epoxy system to resin and nett stone materials. The use of this epoxy system is particularly suitable where high transparency, high penetration and slow hardening times are required or for the creation of small masses of resin.



LOW VISCOSITY



MEDIUM HARDNESS



GOOD REACTIVITY TO COLD

Technical data:

- ◆ **Viscosity at 25°C:** 450-650 cps
- ◆ **Standard colour:** 1 gardner max
- ◆ **Appearance:** clear matt liquid



Natural stone

How to apply it:

- ◆ Weigh the required quantity in WEIGHT from the two containers.
- ◆ Comply with the ratio between Epoxart A and Epoxart B as indicated in the TDS.
- ◆ When mixing, use clean scales and tools.
- ◆ If necessary, add liquid or pigment dyes before mixing with Part B.
- ◆ Make sure that the material on which the product will be applied is clean and dry.
- ◆ To clean tools soiled with resin, use non-greasy solvents, e.g. Acetone or Butyl Acetate.
- ◆ Use the necessary PPE.
- ◆ Read the technical and safety data sheet carefully.
- ◆ Close the containers with their original caps for correct storage.
- ◆ Avoid prolonged contact with air.

Performance:

Gel time in mass at 25°C	150-180 min
Workability time at 25°C	24-48 h
Mixing ratio	3:1
Stability to sunlight	good

Safety measures:

Before use, please read the instructions in the safety data sheet and the notes on the packaging. Close the container after use. For professional use only.

Warnings:

When a surface is treated for the first time, it is advisable to evaluate its effect or adhesion on a sample or hidden corner.